

IN THE CLAIMS:

The listing of claims will replace all prior versions, and listing, of claims in the application.

1. (Currently Amended) A polycarbonate composition comprising:
 - (A) an aromatic polycarbonate and/or polyester-carbonate;
 - (B) a graft polymer; and
 - (C) 1 to 3 %, relative to the weight of the composition, of a copolymer of styrene and at least one monomer containing at least one carboxyl group, the copolymer having a weight average molecular weight, M_w , equal to or greater than 10,500 g/mol.
2. (Currently Amended) The composition according to Claim 1, wherein (C) is present in an amount of ~~0.4 to 7~~ 1.5 to 2.5 % relative to the weight of the composition.
3. (Cancelled)
4. (Original) The composition according to Claim 1 wherein (C) is a copolymer of styrene and maleic anhydride.
5. (Currently Amended) The composition according to Claim 4, wherein (C) ~~contains~~ comprises maleic anhydride in an amount of 1 to 40 % relative to the weight of (C).
6. (Original) The composition according to Claim 1 wherein the weight average molecular weight of (C) is 10,500 to 300,000.
7. (Original) The composition according to Claim 1 wherein (A) is present in an amount of 5 to 98 % relative to the weight of the composition.

8. (Original) The composition according to Claim 1 wherein (A) is present in an amount of 4 to 75 % relative to the weight of the composition.

9. (Original) The composition according to Claim 1 wherein (B) is a graft of B.1) 5 to 95 wt.% of one or more vinyl monomers on B.2) 95 to 5 wt.% of one or more graft bases having glass transition temperatures lower than 10°C.

10. (Original) The composition according to Claim 1 wherein (B) is present in an amount of 1 to 94 % relative to the weight of the composition.

11. (Original) The composition according to Claim 1 wherein (B) is present in an amount of 5 to 60 % relative to the weight of the composition.

12. (Currently Amended) The composition according to Claim 1 further containing comprising component (D) selected from at least one of thermoplastic vinyl (co)polymer and/or polyalkylene terephthalate.

13. (Original) The composition according to Claim 12 wherein D is present in an amount of 0 to 25 % relative to the weight of the composition.

14. (Currently Amended) The composition according to Claim 1 further containing comprising (E) at least one additive selected from the group consisting of flameproofing agents, fluorinated polyolefins and inorganic particles.

15. (Original) The composition of Claim 14 wherein inorganic particles are selected from the group consisting of talc, mica, wollastonite, quartz, and titanium dioxide.

16. (Original) A process for the preparation of the composition of Claim 1 comprising mixing (A), (B) and (C) and subjecting the resulting mixture to melt compounding and melt extrusion at temperatures of 200 to 300°C in conventional units.

17. (Original) A method of using the composition of Claim 1 comprising producing a molded article.

18. (Original) The molded article prepared by the method of Claim 17.

19. (Currently Amended) A multi-layered composite comprising at least one first layer that includes the composition of Claim 1 and a second layer that ~~contains~~ comprises polyurethane.

20. (Original) The composite of Claim 19, wherein said first layer is bonded directly to said second layer.

21. (Original) The composite of Claim 20 wherein said second layer is a polyurethane foam.

22. (Original) The composite of Claim 20 wherein said second layer is a solid polyurethane.

23. (Currently Amended) The composite of Claim 20 further comprising at ~~least one~~ an additional polymeric layer, said additional polymeric layer being bonded directly to said second layer.

24. (Currently Amended) The composite of Claim 23, wherein the additional polymeric layer ~~contains~~ comprises polyvinyl chloride.

25. (Cancelled)

26. (New) A multi-layered composite comprising

- (i) at least one first layer that includes a polycarbonate composition comprising,
 - (A) an aromatic polycarbonate and/or polyester-carbonate;
 - (B) a graft polymer; and

- (C) 0.4 to 7 %, relative to the weight of the composition, of a copolymer of styrene and at least one monomer containing at least one carboxyl group, the copolymer having a weight average molecular weight, M_w , equal to or greater than 10,500 g/mol; and
- (ii) a second layer comprising polyurethane.

27. (New) The multi-layered composite of Claim 26 wherein said polycarbonate composition contains said copolymer (C) in an amount of 1.5 to 2.5 %, relative to the weight of said composition.